



Product Data Sheet

SYLVARES™ SA 85

FEATURES

- Water white colour
- Low odour and volatility
- Compatibility with EVA
- Improve strength + heat resistance

APPLICATIONS

- Packaging
- Bookbinding
- Sealant
- Pressure Sensitive Adhesives
- Non wovens

PROPERTIES	SPECIFICATIONS
Softening Point, Ring & Ball, °C	80-90
Colour, Gardner 63, 1:1 in toluene	Max. 60
	TYPICAL VALUES
Colour 8h, 180 °C, Hazen	60
Colour 24h, 180 °C, Hazen	120
Viscosity, 140 °C, dPa·s	10
Viscosity, 180 °C, dPa·s	1
Loss in weight 24h, 180 °C, %	5
Glass transition temp. °C (DSC)	43

DELIVERY FORM	The product is delivered as flakes in 25 kg paper bags.
STORAGE CONDITIONS	We recommend that the product should be stored under dry conditions. The storage temperature should not exceed 25 °C. Maximum storage time: 6 months.
GERMAN REGUL. STATUS	SYLVARES™ SA 85 fulfils the requirements in "Lebensmittel- und Bedarfsgegenständegesetz Paragraph 30 und 31" as well as "BGA Empfehlung XXV".
CN CODE	3903.90 00



Arizona Chemical, PO Box 60053, 1320 AB Almere, The Netherlands
Telephone +31 36 546 2800 Telefax +31 36 546 2811 Web www.arizonachemical.com

Revision 2 September 2010

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification.