



Product Data Sheet

Revision Date: 04/08

AQUATAC® 6025

Dispersion

AQUATAC® 6025 dispersion is a low softening point waterborne tackifier for pressure sensitive adhesives. **AQUATAC® 6025** can be used with higher softening point tackifiers to improve low temperature adhesion.

| PROPERTIES* | TYPICAL | SPECIFICATIONS |
|---|-------------|----------------|
| Solids Content, % | 61 | 59.5 – 62.5 |
| Viscosity, RVT Brookfield, 20 rpm, 25 °C, cps | 5,700 | 3,000 – 8,000 |
| Weight Per Gallon | 8.8 | |
| pH | 7.6 | 6 – 8 |
| Particle Size, Mean, Microns | 1.9 | 2.5 Maximum |
| Appearance | Milky White | |

| BASE RESIN PROPERTIES* | TYPICAL | SPECIFICATIONS |
|------------------------|---------|----------------|
| Acid Number | 22 | 20 – 24 |
| Softening Point, °C | 26 | 23 – 29 |
| Color, Gardner, Neat | 4- | 7 Maximum |

| | |
|--|---|
| Shipping Data: | AQUATAC® 6025 is available in liquid in drums, totes, and bulk. |
| Food and Drug Administration Coverage | AQUATAC® 6025 meets the ingredient requirements of the following section of the Code of Federal Regulations, Title 21 when used according to the regulations and any limitations that may apply: 175.105 Adhesives |

*Arizona Chemical Test Methods available on request



Technical Service: Savannah, GA (912) 238-6556
Sales Service: Jacksonville, FL - (800) 733-1374

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.