



Product Data Sheet

SYLVARES® TP 2040HM

Terpene Phenolic Resin

SYLVARES® TP 2040HM Resin is a terpene phenolic resin. This thermoplastic resin has a high terpene level, which exhibits excellent tackifying, flexibility, and compatibility properties for use in numerous polymers for adhesives.

SPECIFICATIONS*

Softening Point, Ring & Ball, °C	122 - 128
Color, Solid, Gardner	6 Maximum

TYPICAL PROPERTIES*

Softening Point, Ring & Ball, °C	125
Color, Solid, Gardner	4+
Melt Viscosity, Brookfield, cps at 150°C (302°F)	7815
at 177°C (350°F)	400
at 170°C (374°F)	145
Pounds per Gallon, 25°C	8.5

Recommended Uses:	SYLVARES® TP 2040HM Resin is used in packaging hot-melt adhesives, bookbinding and as a co-tackifier.
Soluble in:	SYLVARES® TP 2040HM Resin is soluble in aliphatic, aromatic and chlorinated hydrocarbons, esters, terpenes, ethyl ether, and some alcohols. It is insoluble in glycols, ketones and most alcohols.

*Arizona Chemical Test Methods available on request.



Technical Service: Savannah, GA (912) 238-6556
Sales Service: Jacksonville, FL - (800) 733-1374

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.



Product Data Sheet

SYLVARES® TP 2040HM

Terpene Phenolic Resin

Compatible with:	This resin is compatible with ethylene-based copolymer resins.
FDA Status:	SYLVARES® TP 2040HM Resin meets the ingredient requirements of the following section of the Code of Federal Regulations, Title 21 when used according to the regulations and any limitations that may apply: 175.105 Adhesives 175.125 Pressure Sensitive Adhesives
DOT Shipping Classification:	Non-hazardous.
Shipping:	Flaked in multi-wall bags, 50 lb. net.
Storage:	Store under ambient conditions; minimize exposure to heat during storage.

1/05



Technical Service: Savannah, GA (912) 238-6556
Sales Service: Jacksonville, FL - (800) 733-1374

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.